

Chemical Resistance

- HIGH RESISTANCE** (corrosion-proof) - all materials belonging to this class are completely or almost completely corrosion-proof against the conveyed fluid, according to the specified operating conditions.
- LIMITED RESISTANCE** - the materials belonging to this class are partially attacked by the conveyed chemical compound. The average life of the material is therefore shorter, and it is advisable to use a higher safety factor by selecting a higher SN rating pipe.
- NO RESISTANCE** - all material belonging to this class are subject to corrosion by the conveyed fluid and they should therefore not be used.

The absence of any class indication means that no data are available concerning the chemical resistance of the material in respect of the conveyed fluid.

ABBREVIATIONS

sat = saturated solution at 20°C, **nd** = undefined concentration,
deb = weak concentration, **comm** = commercial solution. **dil** = diluted solution

	FORMULA	CONC %	TEMP (°C)	PE		FORMULA	CONC %	TEMP (°C)	PE								
ACETALDEHYDE	CH ₃ CHO	100	25 60	1	- FLUORIDE	NH ₄ F	25	25 60	1 1								
- AQUEOUS SOLUTION		40	25 60	1 2		- HYDROXIDE	NH ₄ OH	28	25 60	1 1							
ACETIC ACID	CH ₃ COOH	≤ 25	25 60	1 1			- NITRATE	NH ₄ NO ₃	sat	25 60	1 1						
		30	25 60	1 1				- PHOSPHATE DIBASIC	NH ₄ (HPO ₄) ₂	all	25 60	1 1					
		60	25 60	1 1					- PHOSPHATE META	(NH ₄) ₄ P ₄ O ₁₂	all	25 60					
- GLACIAL		80	25 60	1 2						- PHOSPHATE TRI	(NH ₄) ₂ HPO ₄	all	25 60				
ACETIC ANHYDRIDE	(CH ₃ CO) ₂ O	100	25 60	2 2							- PERSULFATE	(NH ₄) ₂ S ₂ O ₈	all	25 60			
ACETONE (DIMETHYL KETONE)	CH ₃ COCH ₃	10	25 60	1 2								- SULFIDE	(NH ₄) ₂ S	deb sat	25 25 60 60	1 1 1 1	
		100	25 60	2 2									- SULFHYDRATE	NH ₄ OHSO ₄	dil sat	25 60 25 60	1 1 1 1
ACETOPHENONE (ACETYL BENZENE OR PHENYL METHYL KETONE)	CH ₃ COC ₆ H ₅	nd	25 60											AMYLCETATE (PENTYL ACETATE)	CH ₃ CO ₂ CH ₂ (CH ₂) ₃ CH ₃	100	25 60
ACRYLONITRILE (ACRYLONITRILE OR VINYL CYANIDE)	CH ₂ CHCN	technically pure	25 60	1 1	AMYLCALCOHOL									CH ₃ (CH ₂) ₃ CH ₂ OH	nd	25 60	1 1
ADIPIC ACID AQUEOUS SOLUTION	(CH ₂ CH ₂ CO ₂ H) ₂	sat.	25 60	1 1	ALNILINE (PHENYLAMINE OR AMINOBENZENE) - CHLORHYDRATE (ANILINE HYDROCHLORIDE)	C ₆ H ₅ NH ₂ CH ₆ H ₅ NH ₂ HCl								all nd	25 25 60 60	2 2 2 2	
ALLYL ALCOHOL	CH ₂ CHCH ₂ OH	96	25 60	1 2	ANTIMONY - TRICHLORIDE	SbCl ₃	100							25 60	1 1		
ALUM AQUEOUS SOLUTION (POTASH ALUM.SOL.)	Al ₂ (SO ₄) ₃ K ₂ SO ₄ ·H ₂ O	dil dil sat.	25 60 60	1 1 1	ANTHRAQUINONE (SULFONIC ACID)	suspension	25	1 60						- -			
ALUMINIUM - CHLORIDE	AlCl ₃	all	25 60	1 1	AQUA REGIA	HCl+HNO ₃	100	25 60	3 3								
- FLORIDE	AlF ₃	100	25 60	1 1	ARSENIC ACID	H ₃ ASO ₄	deb 80	25 60 25 60	1 1 1 1								
- HYDROXIDE	Al(OH) ₃	all	25 60	-	BARIUM CARBONATE - CHLORIDE	BAC ₃ BaCl ₂	all 10	25 60 25 60	1 1 1 1								
NITRATE	Al(NO ₂) ₃	nd	25 60	-	- HYDROXIDE	Ba(OH) ₂	all	25 60	1 1								
SULFATE	Al(SO ₄) ₃	deb sat.	25 60 25 60	1 1 1 1	- SULFATE	BaSO ₄	nb	25 60	1 1								
AMMONIA - AQUEOUS SOLUTION	NH ₃	deb sat	25 60 25 60	1 1 1 1	- SULFIDE	BaS	sat	25 60									
- DRY GAS		100	25 60	1 1	BEER		comm	25 60	1								
- LIQUID		100	25 60	1 1	BENZALDEHYDE	C ₆ H ₅ CHO	nd	25 60	2 2								
AMMONIUM - ACETATE	CH ₃ COONH ₄	sat.	25 60	1 1													
- CARBONATE	(NH ₄) ₂ CO ₃	all	25 60	1 1													

Chemical Resistance

	FORMULA	CONC %	TEMP (°C)	PE		FORMULA	CONC %	TEMP (°C)	PE
BENZENE (BENZOL)	C ₆ H ₆	100	25 60	3	CHLORAMINE	NH ₂ Cl	dil	25 60	1
- + LIGROIN		20/80	25 60		CHLORIC ACID	HClO ₃	20	25 60	1 3
- MONOCHLORINE	C ₆ H ₃ Cl	technically pure	25 60	2	CHLORINE	Cl ₂	sat	25 60	
BENZOIC ACID	C ₆ H ₅ COOH	sat	25 60	1 1	- DRY GAS		10 100	25 60 25 60	
BENZYL ALCOHOL	C ₆ H ₅ CH ₂ OH	100	25 60		- WET GAS		5 g/m ³ 10 g/m ³ 66 g/m ³	25 60 25 60 25 60	2 2
BORIC ACID (BORACIC ACID)	H ₃ BO ₃	deb sat	25 60 25 60	1 1 1 1	- LIQUID		100	25 60	3
BRINE		comm	25 60		CHLOROACETIC ACID	ClCH ₂ COH	85 100	25 60 25 60	2 3 3 3
BROMIC ACID	HBrO ₃	10	25 60	1 1	CHLOROBENZENE	C ₆ H ₅ Cl	all	25 60	
BROMINE - LIQUID - VAPOURS	Br ₂	100	25 60	3 3	CHLOROFORM	CHCl ₃	all	25 60	2
BUTADIENE	C ₄ H ₆	100	25 60	3	CHLOROSULPHONIC ACID	ClHSO ₃	100	25 60	3 3
BUTANEDIOL AQUEOUS	CH ₃ CH ₂ CHOHCH ₂ OH	10 concentrated	25 60 25 60	1 2 3	CHROME ALUM	KCr(SO ₄) ₂	nd	25 60	1 1
BUTANE GAS	C ₄ H ₁₀	10	25 60	1 1	CHROMIC ACID	CrO ₃ +H ₂ O	10 30 50	25 60 25 60 25 60	2 3 2 3 3
BUTYL - ACETATE (BUTANATE) - ALCOHOL (BUTANOL) - PHENOL	CH ₃ CO ₂ CH ₂ CH ₂ CH ₂ CH ₃ C ₄ H ₉ OH C ₄ H ₉ C ₆ H ₄ OH	100	25 60 25 60	3 3 3	CHROMIC SOLUTION	CrO ₃ +H ₂ O+H ₂ SO ₄	50/35/15	25 60	3 3
BUTYLENE GLYCOL	C ₄ H ₈ (OH) ₂	100	25 60	1 1	CITRIC ACID AQUEOUS SOLUTION	C ₃ H ₄ (OH)(CO ₂ H) ₃	50	25 60	1 1
BUTYRIC ACID (BUTANOIC ACID)	C ₂ H ₅ CH ₂ COOH	20 concentrated	25 60 25 60	1 2 3 3	COPPER - CHLORIDE - CYANIDE	CuCl ₂ CuCN ₂	sat all	25 60 25 60	1 1
CALCIUM - BISULFITE - CARBONATE - CHLORATE - CHLORIDE - HYDROXIDE - HYPOCHLORITE - NITRATE - SULFATE - SULFIDE	Ca(HSO ₃) ₂ CaCO ₃ CaHCl CaCl ₂ Ca(OH) ₂ Ca(OHl) ₂ Ca(NO ₃) ₂ CaSO ₄ CaS	nd all nd all all 50 nd sat	25 60 25 60 25 60 25 60 25 60	1 1 1 1 1 1 1 1 2 2	- FLUORIDE - NITRATE - SULFATE	CuF ₂ Cu(NO ₃) ₂ CuSO ₄	all nd dil sat	25 60 25 60 25 60 25 60	1 1 1 1 1 1 1
CAMPHOR OIL		nd	25 60	3 3	COTTONSEED OIL		comm	25 60	
CARBON - DIOXIDE AQUEOUS SOLUTION - GAS - DISULFIDE - MONOXIDE - TETRACHLORIDE	CO ₂ CS ₂ CO CCl ₄	- 100 100 100	25 60 25 60 25 60	1 1 1 2 1 1 2 3	CRESOL (HYDROXY TOLUENE)	CH ₃ C ₆ H ₄ OH	≤90 ≥90	25 60 25 60	1
CARBONIC ACID - AQUEOUS SOLUTION - DRY - WET	H ₂ CO ₃	sat 100 all	25 60 25 60 25 60	1 1 1 1 1 1	CRESYLIC ACID	CH ₃ CH ₆ H ₄ COOH	50	25 60	
CARBON OIL		comm	25 60		CYCLOHEXANE	C ₆ H ₁₂	all	25 60	1
					CYCLOHEXANONE	C ₆ H ₁₀ O	all	25 60	1
					DECAHYDRONAFTALENE	C ₁₀ H ₁₈	nd	25 60	1 2
					DEMINEALIZED WATER		100	25 60	1 1
					DIBUTYPATHALATE	C ₆ H ₄ (CO ₂ C ₄ H ₉) ₂	100	25 60	3
					DICHLORO-ACETIC ACID	Cl ₂ CHCOOH	100	25 60	1 2
					DICHLOROETHANE (ETHYLENE DICHLORIDE)	CH ₂ ClCH ₂ Cl	100	25 60	3 3
					DICHLOROETHYLENE	Cl(CH ₂) ₂ Cl	100	25 60	3 3
					DIETHYL ETHER	C ₂ H ₅ OC ₂ H ₅	100	25 60	3 3
					DIGLYCOLIC ACID	(CH ₂) ₂ Cl(CO ₂ H) ₂	18	25 60	1 1
					DIMETHYLAMINE	(CH ₃) ₂ NH	100	25 60	2

Chemical Resistance

	FORMULA	CONC %	TEMP (°C)	PE		FORMULA	CONC %	TEMP (°C)	PE
DI-OCTYLPHTHALATE		all	25 60	1 2	HYDROCHLORIC ACID (MURIATIC ACID)	HCl	≤25	25 60	1 1
DISTILLED WATER		100	25 60	1 1			≤37	25 60	1 2
DRINKING WATER		100	25 60	1 1	HYDROCYANIC ACID (PRUSSIC ACID OR HYDROGEN CYANIDE)	HCN	deb	25 60	1 1
ETHERS		all	25 60				HYDROFLUORIC ACID	HF	10
ETHYL - ACETATE (ACETIC ETHER) - ALCOHOL (ETHANOL) - CHLORIDE - ETHER	CH ₃ CO ₂ C ₂ H ₅	100	25 60	1 3	HYDROGEN	H ₂	all	25 60	
	CH ₃ CH ₂ OH	nd	25 60	1 2	HYDROGEN - PEROXIDE (BLEACH)	H ₂ O ₂	30	25 60	1 1
	CH ₃ CH ₂ Cl	all	25 60	2			50	25 60	2 -
	CH ₃ CH ₂ OCH ₂ CH ₃	all	25 60		- SULFIDE DRY		sat	25 60	1 1
ETHYLENE - CHLOROHYDRIN - GLYCOL (ETHANEDIOL OR GLYCOL)	CICH ₂ CH ₂ OH	100	25 60		- SULFIDE WET		sat	25 60	1 1
FATTY ACIDS		nd	25 60		HYDROSUPHITE		≤10	25 60	
					HYDROXYLAMINE SULPHATE	(H ₂ NOH) ₂ H ₂ SO ₄	12	25 60	1
FERRIC - CHLORIDE	FeCl ₃	10	25 60		ILLUMINATING GAS		100	25 60	1
		sat	25 60	1 1	IODINE - DRY AND WET - TINCTURE	I ₂	3	25 60	
- NITRATE	Fe(NO ₃) ₃	nd	25 60	1 1			≤3	25 60	2 3
- DEXTRINE (BRITISH GUM OR STARCH GUM) - SULFATE	C ₆ H ₁₂ OCH ₂ O	nd	25 60	1 1	ISOCTANE	C ₈ H ₁₈	100	25 60	2
		Fe(SO ₄) ₃	nd	25 60	1 1	ISO-OCTANE	(CH ₃) ₃ CCH ₂ (CH ₃) ₂		
FERROUS - CHLORIDE - SULFATE	FeCl ₂	sat	25 60	1 1	ISOPROPYL - ETHER	(CH ₃) ₂ CHOCH(CH ₃) ₂	100	25 60	2 3
		FeSO ₄	nd	25 60	1 1	- ALCOHOL (ISOPROPANOL)	(CH ₃) ₂ CHOH	100	25 60
FERTILIZER		≤ 10	25 60	1 1	LACTIC ACID	CH ₃ COHCOOH	≤28	25 60	1 1
		sat	25 60	1 1	LANOLINE		nd	25 60	1
FLUORINE GAS DRY	F ₂	100	25 60	2 3	LEAD ACETATE	Pb(CH ₃ COO) ₂	sat	25 60	1 -
FLUROSILICIC ACID	H ₂ SiF ₆	32	25 60	1 1	LINSEED OIL		comm	25 60	2
FORMALDEHYDE	HCOH	-	25 60	1 1	LUBRICATING OILS		comm	25 60	3
FORMIC ACID	HCOOH	50	25 60	1 1	MAGNESIUM - CARBONATE - CHLORIDE	MgCO ₃	all	25 60	
		100	25 60	1 1		MgCl ₂	sat	25 60	1 1
FRUIT PULP AND JUICE		comm	25 60	1	- HYDROXIDE	Mg(OH) ₂	all	25 60	
FUEL OIL		100	25 60		- NITRATE	MgNO ₃	nd	25 60	1 1
		comm	25 60	- 2	- SULFATE	MgSO ₄	dil	25 60	1 1
FURFUROLE ALCOHOL	C ₆ H ₃ OCH ₂ OH	nd	25 60	2 2		sat	25 60	1 1	
GAS EXHAUST - ACID - WITH NITROUS - VAPOURS		all	25 60		MALEIC ACID	COOHCHCHCOOH	nd	25 60	1 1
		traces	25 60	1 1	MALIC ACID (HYDROXYSUCCINIC ACID)	CH ₂ CHOH(COOH) ₂	nd	25 60	1 -
GAS PHOSGENE	ClCOCl	100	25 60	2 2	MERCURIC - CHLORIDE	HgCl ₂	sat	25 60	1 1
GELATINE		100	25 60	1 -	- CYANIDE	HgCN ₂	all	25 60	
					MERCUROS NITRATE	HgNO ₃	nd	25 60	1 1
GLUCOSE (DEXTROSE)	C ₆ H ₁₂ O ₆	all	25 60	1 1	MERCURY	Hg	100	25 60	1 1
GLYCERINE AQ. SOL.(GLYCEROL)	HOCH ₂ CHOHCH ₂ OH	all	25 60	1 1	METHYL - ACETATE - ALCOHOL (METHANOL OR WOODSPIRIT) - BROMIDE (BROMOMETHANE) - CHORIDE (CHLOROMETHANE) - ETHYLKETONE	CH ₃ COOCH ₃	100	25 60	- -
GLYCOGLUE AQUEOUS		10	25 60	1 1		CH ₃ OH	nd	25 60	1
GLYCOLIC ACID	HOCH ₂ COOH	37	25 60	1 1		CH ₃ Br	100	25 60	3
HEPTANE	C ₇ H ₁₆	100	25 60	3		CH ₃ Cl	100	25 60	1
HEXANE	C ₆ H ₁₄	100	25 60	1 2	- ETHYLKETONE	CH ₃ COCH ₂ CH ₃	all	25 60	1 2
					METHYLAMINE	CH ₃ NH ₂	32	25 60	1 2
HYDROBROMIC ACID	HBr	≤10 48	25 60 25 60	1 1 1 1					

Chemical Resistance

	FORMULA	CONC %	TEMP (°C)	PE		FORMULA	CONC %	TEMP (°C)	PE	
METHYLENE CHLORIDE (DICHLOROMETHANE)	CH ₂ Cl ₂	100	25 60	3			≤85	25 60	1 2	
METHYL SULPHURIC ACID	CH ₃ COOSO ₄	50	25 60	2 2	- ANHYDRIDE	P ₂ O ₅	nd	25 60	1 1	
		100	25 60	3 3		PHOSPHORUS TRICHLORIDE	PCl ₃	100	25 60	1
MILK		100	25 60	1		PHOTOGRAPHIC - DEVELOPER		comm	25 60	
MINERAL ACID/DOULOUS WATER		nd	25 60	1 1		- EMULSION		comm	25 60	1
MOLASSES		comm	25 60	1 2		PHTHALIC ACID	C ₆ H ₄ (CO ₂ H) ₂	50	25 60	1 1
NAPHTA		100	25 60	2 3		PICRIC ACID	HOC ₆ H ₂ (NO ₂) ₃	1	25 60	1 -
NAPHTALINE		100	25 60	1	(2,4,6 TRINITROPENOL)		≥1	25 60	1	
NICKEL - CHLORIDE	NiCl ₃	all	25 60	1 1	POTASSIUM - BICHROMATE (POTASSIUM HYDROGENCARBONATE)	K ₂ Cr ₂ O ₇	40	25 60	1	
- NITRATE	Ni(NO ₃) ₂	nd	25 60	1 1	- BORATE	K ₃ BO ₃	sat	25 60		
- SULFATE	NiSO ₄	dil sat	25 60 25 60	1 2 1 1	- BROMATE	KBrO ₃	nd	25 60		
NITRIC ACID	HNO ₃	anhydrous	25 60		- BROMIDEKBr		sat	25 60	1	
		20	25 60	1 2	- CARBONATE (POTASH)	K ₂ CO ₃	sat	25 60	1 1	
		40	25 60	- 2	- CHROLIDE (POTASSIUM MURIATE)	KCl	sat	25 60	1 1	
		60	25 60	3 3	- CHROMATE	K ₂ CrO ₄	40	25 60	1 1	
		98	25 60	3 3	- CYANIDE	KCN	sat	25 60	1 1	
NITROBENZENE	C ₆ H ₅ NO ₂	all	25 60	2	- FERROCYANIDE	K ₄ Fe(CN) ₆ H ₂ O	100	25 60	1 1	
OLEIC ACID	C ₁₇ H ₃₃ O ₂	comm	25 60	- 2	- FLUORIDE	KF	sat	25 60		
OLEUM (FUMING SULPHURIC) ACID OR PYROSULPHURIC ACID)	H ₂ S ₂ O ₇	nd	25 60	3	- HYDROXIDE (CAUSTIC POTASH)	KOH	≤60	25 60	1 1	
- VAPOURS		low high	25 60 25 60		- NITRATE KNO ₃ (NITRE, SALTPETRE)	sat	25	1 60	1	
OLIVE OIL		comm	25 60	3	- PERBORATE	KBO ₃	all	25 60		
OXALIC ACID	HO ₂ CCO ₂ H	10 sat	25 60 25 60	1 1 1 1	- PERBORATE	KBO ₃	all	25 60		
OXYGEN	O ₂	all	25 60	1 2	- PERMANGANATE (PERMANGANATE OF POTASH)	KMnO ₄	10	25 60	1 1	
OZONE	O ₃	nd	25 60	2 3	- PERSULFATE	K ₂ S ₂ O ₈	nd	25 60	1 1	
PALMITIC ACID	CH ₃ (CH ₂) ₁₄ COOH	10 70	25 60 25 60	- -	- SULFATE	K ₂ SO ₄	sat	25 60	1 1	
PARAFFIN (ALKANE)		nd	25 60	2	PROPANE - GAS	C ₃ H ₈	100	25 60	1	
- EMULSION		comm	25 60	2 2	- LIQUID		100	25 60	2	
- OIL (KEROSENE)		nd	25 60		PROPYL ALCOHOL (PROPANOL)	C ₃ H ₇ OH	100	25 60	1 1	
PERCHLORIC ACID	HClO ₄	100 70	25 60 25 60	1 1 1 2	PYRIDINE	CH(CH ₂) ₂ N	nd	25 60	1 2	
PETROL - REFINED		100	25 60		RAIN WATER		100	25 60	1 1	
- UNREFINED		100	25 60		SEA WATER		100	25 60	1 1	
PHENOL - AQUEOUS SOLUTION (CARBOLIC ACID)	C ₆ H ₅ OH	1 ≤90	25 60 25 60	1 1	SILICIC ACID	H ₂ SiO ₃	all	25 60	1 1	
PHENYL HYDRAZINE	C ₆ H ₅ NHNH ₂	all	25 60	2 2	SILICONE OIL		nd	25 60	1 2	
- CHLORHYDRATE	C ₆ H ₅ NHNH ₃ Cl	sat	25 60	3 1	SILVER - CYANIDE	AgCN	all	25 60		
PHOSPHORIC - ACID	H ₃ PO ₄	≤ 25 ≤50	25 60 25 60	1 1 1 1	- NITRATE	AgNO ₃	nd	25 60	1 1	
					- PLATING SOLUTION		comm	25 60		
					SOAP - AQUEOUS SOLUTION		high	25 60		
					SODIC LYE		≤60	25 60		
					SODIUM - ACETATE	CH ₃ COONa	100	25 60	1 1	

Chemical Resistance

	FORMULA	CONC %	TEMP (°C)	PE		FORMULA	CONC %	TEMP (°C)	PE	
- BICARBONATE (SODIUM HYDROGEN CARBONATE)	NaHCO ₃	nd 60	25 1	1	- FUMING (OLEUM)		60	3		
- BISULFITE	NaHSO ₃	100	25 60	1 1			all	25 60		
- BROMIDE	NaBr	sat	25 60			- NITRIC AQUEOUS SOLUTION	H ₂ SO ₄ +HNO ₃ +H ₂ O	48/49/3	25 60	3 3
- CARBONATE	Na ₂ CO ₃	sat	25 60	1 1			50/50/0	25 60	3 3	
- CHLORATE	NaClO ₃	nd	25 60	1 1			10/20/70	25 60	2 2	
- CHLORIDE	NaCl	dil sat	25 25 60	1 1 1		TALLOW EMULSION		comm	25 60	1 2
- CYANIDE	NaCN	all	25 60			TANNIC ACID	C ₁₄ H ₁₀ O ₉	10	25 60	1 1
- FERROCYANIDE	Na ₄ Fe(CN) ₆	sat	25 60	1 1		TARTARIC ACID	HOOC(CHOH) ₂ COOH	all	25 60	1 1
- FLUORIDE	NaF	all	25 60	1 1		TETRACHLORO - ETHANE	CHCl ₂ CHCl ₂	nd	25 60	2 3
- HYDROXIDE	NaOH	60	25 60	1 1		- ETHYLENE (PERCHLOROETHYLENE)	CCl ₂ CCl ₂	nd	25 60	2 3
- HYPOCHLORITE	NaOCl	deb	25 60	1		TETRAETHYLLEAD	Pb(C ₂ H ₅) ₄	100	25 60	1
- HYPOSULFITE	Na ₂ S ₂ O ₃	nd	25 60			TETRAHYDROFURAN	C ₄ H ₈ O	all	25 60	2 3
- NITRATE	NaNO ₃	nd	25 60	1 1		THIONYL CHLORIDE	SOCl ₂	-	25 60	3
- PERBORATE	NaBO ₃ H ₂ O	all	25 60			THIOPHENE	C ₄ H ₄ S	100	25 60	2 2
- PHOSPHATE di	Na ₂ HPO ₄	all	25 60			TOLUENE	C ₆ H ₅ CH ₃	100	25 60	2 3
- PHOSPHATE tri	Na ₃ PO ₄	all	25 60	1 1		TRANSFORMER OIL		nd	25 60	1 2
- SULPHATE	Na ₂ SO ₄	dil sat	25 60 25 60	1 1 1 1		TRICHLORO- ACETIC ACID	CCl ₃ COOH	≤50	25 60	1 2
- SULFIDE	Na ₂ S	dil sat	25 60 25 60	1 1 1 1		TRICHLOROETHYLENE	C ₂ ClCHCl	100	25 60	2 2
- SULFITE	NaSO ₃	sat	25 60			TRIETHANOLAMINE	N(CH ₂ CH ₂ OH) ₃	100	25 60	1
STANNIC CHLORIDE	SnCl ₄	sat	25 60	1 1		TURPENTINE		100	25 60	2 3
STANNOUS CHLORIDE	SnCl ₂	dil	25 60	1 1		UREA AQUEOUS SOLUTION	CO(NH ₂) ₂	≤ 10 33	25 60 25 60	1 1 1 1
STEARIC ACID	CH ₃ (CH ₂) ₁₆ CO ₂ H	100	25 60	2		URINE		nd	25 60	1 1
SUGAR SYRUP		high	25 60	1 1		URIC ACID	C ₅ H ₄ N ₄ O ₃	10	25 60	
SULPHUR	S	100	25 60			VASELINE OIL		100	25 60	1 2
- DIOXIDE AQUEOUS	SO ₂	sat	25 60	1		VINYL ACETATE	CH ₃ CO ₂ CHCH ₂	100	25 60	
- DIOXIDE DRY		all	25 60	1 1		WHISKEY		comm	25 60	
- DIOXIDE LIQUID		100	25 60	1 2		WINES		comm	25 60	1
- TRIOXIDE	SO ₃	100	25 60	3 3		WINE VINEGAR		comm	25 60	1 1
SULPHURIC ACID	H ₂ SO ₄	≤ 10 ≤75 ≤90 ≤96	25 60 25 60 25 60 25 60	1 1 2 2 2 2 2 2	ZINC - CHLORIDE	ZnCl ₂	dil sat	25 60 25 60	1 1 1 1	
					- CHROMATE	ZnCrO ₄	all	25 60		
					- CYANIDE	Zn(CN) ₂	all	25 60		
					- NITRATE	Zn(NO ₃) ₂	nd	25 60		
					- SULFATE	ZnSO ₄	dil sat	25 60 25 60	1 1 1 1	